



9000 1K PU WINDSCREEN

ET/W-9000, 310ml black



Product

1K fast curing polyurethane adhesive for the bonding of vehicle glass and windscreens, side and rear windows.



Surface Preparation

Apply on clean, dry and dust and rust free surfaces. Use Etalon Primer ET/P-901 when required.

Application Conditions

+5°C +40°C

Hardness shore

A 57 DIN 53505

Tensile strength

12± 0,1 N/mm² DIN 53504

Elongation at break

≥700% DIN 53504

Specific weight

1,24± 0,02gr/cc



Drying

Drive away time on vehicles fitted with both driver and passenger air bags:
2 hours

Shelf life

12 months